

MATERIAL DATASHEET

DMH 120 C-HPU

Mechanical, Physical and Thermal Properties

thermoplastic polyurethane with resistance to hydrolysis

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				red		red
hardness	23°C	ISO 868	Shore A	96 ± 2	Shore A	96 ± 2
hardness	23°C/3 sek.	ISO 868	Shore D	50 ± 3	Shore D	50 ± 3
hardness	23°C/15 sek.	ISO 868	Shore D	48 ± 3	Shore D	48 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 11	psi	≥ 1595
modulus 300 %	23°C	DIN 53 504	MPa	≥ 22	psi	≥ 3190
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6525
elongation at break	23°C	DIN 53 504	%	≥ 450	%	≥ 450
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 80	lbf/inch	≥ 450
spec. gravity	23°C	ISO 1183	kg/m ³	1110 ± 20	g/cm ³	1,11± 0,02
abrasion		DIN 53 516	mm ³	20	mm ³	20
compression set	*	ISO 815	%	≤ 30	%	≤ 30
compression set	**	ISO 815	%	≤ 35	%	≤ 35
minimum service temperature			°C	-37	°F	-35
maximum service temperature			°C	110	°F	230

* 24h 70°C 25% def. ** 24h 100°C 25% def. *** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on aromatic isocyanate and diols

Resistant to oil, water, ozone, microbes

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

Foodstuff approval	in accordance with FDA CFR 21-177.2600
revision: 03-2024	

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH

DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11

8772 Traboch, Österreich

+43 833 200 60 0

