

MATERIAL DATASHEET

Mechanical, Physical and Thermal Properties

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour			Shore A	blue		blue
hardness		ISO 868			Shore A	
hardness	23°C/3 sek.	ISO 868	Shore D	57 ± 3	Shore D	57 ± 3
hardness	23°C/15 sek	ISO 868	Shore D	53 ± 3	Shore D	53 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 17	psi	≥ 2465
modulus 300 %	23°C	DIN 53 504	MPa	≥ 33	psi	≥ 4785
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6525
elongation at break	23°C	DIN 53 504	%	≥ 350	%	≥ 350
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 110	lbf/inch	≥ 630
spec. gravity	23°C	ISO 1183	kg/m ³	1140	g/cm ³	1,14
abrasion		DIN 53 516	mm ³	25	mm ³	25
compression set	*	ISO 815	%	≤ 40	%	≤ 40
compression set		ISO 815	%		%	
minimum service temperature			°C	-55	°F	-67
temp. max hot air, short			°C	110	°F	230

* 24h 70°C 25% def. ** 24h 100°C 25% def. *** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on aromatic isocyanate and diols

Resistant to oil, water, ozone, microbes

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

revision: 03-2024

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH

DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11

8772 Traboch, Österreich

+43 833 200 60 0

