

MATERIAL DATASHEET

TPU with higher temperature stability

Mechanical, Physical and Thermal Properties

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour			Shore A	Orange		Orange
hardness	23°C	ISO 868		94 ± 2	Shore A	94 ± 2
hardness	23°C/3 sek.	ISO 868	Shore D	45 ± 3	Shore D	45 ± 3
hardness	23°C/15 sek.	ISO 868	Shore D		Shore D	
modulus 100%	23°C	DIN 53 504	MPa	≥ 11	psi	≥ 1595
modulus 300 %	23°C	DIN 53 504	MPa	≥ 25	psi	≥ 3625
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6525
elongation at break	23°C	DIN 53 504	%	≥ 340	%	≥ 340
tear strength		DIN ISO 34-1	kN/m	1190	lbf/inch	
spec. gravity	23°C	ISO 1183	kg/m ³		g/cm ³	1,19
abrasion		DIN 53 516	mm ³		mm ³	
compression set	*	ISO 815	%	≤ 36	%	≤ 36
compression set		ISO 815	%		%	
minimum service temperature			°C	-26	°F	-15
maximum service temperature			°C	135	°F	275

* 24h 70°C 25% def. ** 24h 100°C 25% def. *** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on aromatic isocyanate and diols and internal lubricants
 Resistant to oil, hot water, hot air, ozone
 Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

revision: 08-2024

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH

DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11
 8772 Traboch, Österreich
 +43 833 200 60 0

