

MATERIAL DATASHEET

DMH 361 TFE/P 90A

Mechanical, Physical and Thermal Properties

Fluoro Rubber (FEPM)

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour			Shore A	black		black
hardness	23°C/3 sek.	ISO 868		90 ± 5	Shore A	90 ± 5
hardness		ISO 868	Shore A		Shore A	
modulus 100%	23°C	DIN 53 504	MPa	≥ 5,5	psi	≥ 795
tensile strength	23°C	DIN 53 504	MPa	≥ 10	psi	≥ 1450
elongation at break	23°C	DIN 53 504	%	≥ 90	%	≥ 90
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 5	lbf/inch	≥ 28
spec. gravity	23°C	ISO 1183	kg/m³	1630	g/cm³	1,63
rebound elasticity	23°C	DIN 53 512	%	7	%	7
abrasion		DIN 53 516		mm³	mm³	
compression set	*	ISO 815	%	≤ 60	%	≤ 60
compression set		ISO 815	%		%	
compression set		ISO 815	%		%	
minimum service temperature			°C	-5	°F	23
maximum service temperature			°C	200	°F	392
temp. max water/steam			°C	170	°F	338
temp. max hot air, short			°C	230	°F	446

* 24h 70°C 25% def. ** 24h 100°C 25% def. *** 24h 150°C 25% def.

Chemical Properties

Copolymer, based on fluoro

Resistant to: water, steam, greases, crude oil, mineral oil, gasoline, aliphatic and aromatic hydrocarbons, alcohols

Not resistant to: halogenes, ketones and most fluids containing amines

revision: 03-2024

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH

DMH Dichtungs- und Maschinenhandel GmbH

Industriepark West 11

8772 Traboch, Österreich

+43 833 200 60 0

