

MATERIAL DATASHEET

DMH 613 PTFE 25% Glass

Mechanical, Physical and Thermal Properties

25 % clean milled fibres + 75 % virgin PTFE

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				grey		grey
density/specific gravity	23 °C	DIN 53479	kg/m ³	2210	g/cm ³	2,21
hardness	23 °C/3 sek.	ISO 868	Shore D	58 ±3	Shore D	58 ±3
hardness	23°C/15 sek.	ISO 868	Shore D	54 ±3	Shore D	54 ±3
ball indentation hardness	23 °C	DIN 53456 H 135/30	MPa	24 ±5	psi	3480 ±725
tensile strength	23 °C	ASTM D 4745-11a	MPa	≥ 17	psi	≥ 2465
elongation at break	23 °C	ASTM D 4745-11a	%	≥ 170	%	≥ 170
compressive strength	23 °C	DIN 53455	MPa	≥ 8	psi	≥ 1160
thermal conductivity		DIN 52612	$\frac{J * 10^3}{m * h * K}$	≥ 1,3	$\frac{J * 10^3}{m * h * K}$	≥ 1,3
coefficient of thermal expansion	25 °C - 200 °C		K ⁻¹ * 10 ⁻⁵	≥ 10,7	K ⁻¹ * 10 ⁻⁵	≥ 10,7
coefficient of friction *	23 °C		μ	≥ 0,16	μ	≥ 0,16
minimum service temperature			°C	-200	°F	-328
maximum service temperature			°C	260	°F	500
young's modulus		DIN 53457	MPa	1320	psi	191500

* coefficient of friction dry dynamic Steel 16MnCr5 v=0,6m/s; p=0,05 MPa; t=5h

Chemical Properties

Not resistant to halogenides, elemental fluorine, CF₃, molten alkali metals

Foodstuff approval	FDA compliant
revision: 03-2024	

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

DMH

DMH Dichtungs- und Maschinenhandel GmbH
Industriepark West 11
8772 Traboch, Österreich
+43 833 200 60 0

